

## **DP 2700 BONDOFOIL SPECIAL FOIL ADHESIVE**

<b>PRODUCTS</b>	: <b>DP 2700 BONDOFOIL–Special Foil Adhesive</b>
<b>FEATURES</b>	: Excellent binding features, Excellent brightness, Excellent washing fastness, Protects the brightness of the foil, Soft and elastic touching, Grasp the foil perfectly during transfer, Easy to use, Works perfectly in the screen, No chocking even in hot conditions, No losing of features even in high temperature fixings, Complies with ecologic standards.
<b>APPLICATION</b>	: Screen to be printed should be clean and cells should be open, must be applied in plenty of amounts with a soft squeegee.
<b>COLOUR</b>	: Ecu
<b>PH</b>	: $8 \pm 0,5$
<b>VISCOSITY</b>	: (Brookfield25°CSp:7,Rpm:20)60.000–80.000Cp
<b>DENSITY</b>	: 1,08gr/ml
<b>FIXING</b>	: Fixing temperature and time;165°C-170°C, 2minutes.
<b>PRESSING</b>	: Pressing temperature, time and bar;160°C-170°C,5-20 seconds, 5-6 bars. (Type and features of foil should be taken into consideration)
<b>SCREEN</b>	: 34/T-43/T Threads/cm is recommended.
<b>CLEANING</b>	: Screens and other equipments may be cleaned easily by pressure water.
<b>WASHING</b>	: Should be reverse washed under 40C with sensitive program.
<b>PACKING</b>	: Plastic Packing of 10-30kg.

Note : Above mentioned qualified data is obtained from our R&D tests done in our own R&D labs. Supplied as General Knowledge and Information only and should not be considered as a Warranty Information. Printing Quality may change for different company conditions. Please start your production process after completing your own trial tests. Please stir before using the product and keep the product in room temperature.