

CR 2090 SELF CRACK

- PRODUCTS** : CR 2090 SELF CRACK
- FEAUTURES** : Self crack with heat,
Excellent alligator skin effect,
May be coloured,
Soft touchness,
Excellent coverage,
Complies with ecological standards,
- APPLICATION** : To obtaining best effect, all application conditions must be strictly observed. Best cracking effect can be obtained with one 0,5-0,8 mm thickness screen. If double high screen is used, user can not obtain best desired cracking effect. Under these thickness , cracking effect will not occur. After printing, flash cure should be applied on printed design to crack. After getting crack effect on flash cure, fixing process should be done at 165°C twice time 2 minutes or one time 4 minutes. It can be colored with %0.5-1 PG series waterbased pigments. Without any pigment, It will be white after fixing process. 0,5% percentage RB 2601 Superfix Catalyst may be added for a much more increase in washing fastness. Catalyst mixed Ink should be used within 6 hours.
- COLOUR** : Ecrü
- PH** : 6.5 ± 0,5
- VISCOSITY** : (Brookfield 25°C Cp: 7 , Rpm:20) 80.000 – 100.000
- DENSITY** : 1,05 gr / ml
- SCREEN** : 43/T Treads/cm is recommended.
- FIXING** : 165°C-170°C, two times 2 minutes or one time 4 minutes .
- CLEANING** : Screen and other equipments may be cleaned easily by pressure water..
- WASHING** : High washing fastness, high rubbing fastness.
- PACKING** : 10-30 kg plasting packaging

Note : Above mentioned qualified data is obtained from our R&D tests done in our own R&D labs. Supplied as General Knowledge and Information only and should not be considered as a Warranty Information. Printing Quality may change for different company conditions. Please start your production process after completing your own trial tests. Please stir before using the product and keep the product in room temperature.