

SLC SERIES SILICONE INKS

PRODUCTS	: SLC 05 SILICONE CLEAR - Clear silicone pasta
	SLC 15 SILICONE WHITE - White silicone pasta
	SLC 20 SILICONE PUFF - Puff silicone pasta SLC 25 SILICONE BARRIER - Barrier silicone pasta
	SLC 30 SILICONE BRILLSILVER - Silver silicone pasta
	SLC 35 SILICONE BRILLGOLD - Gold silicone pasta
	SLC 40 SILICONE SHINESTAR - Shining silicone pasta
	SLC 45 SILICONE BLUE GREEN VIOLET- Blue/green/violet multicolor
	silicone pasta
	SLC 50 SILICONE PEARL- Pearl silicone pasta
	SLC 55 SILICONE PHOSPHOR - Phosphor silicone pasta
	SLC 60 SILICONE REFLECTCLEAR- Clear reflective silicone pasta
	SLC 65 SILICONE SHINECLEARREFLECT- Shining clear reflective silicone
	pasta SLC 70 SILICONE REFLECTGREY - Grey reflective silicone pasta
	SLC 75 SILICONE BRILLGREYREFLECT- Shininh grey reflective silicone pasta
	SLK 01 SILICONE CATALYST - Silicone catalyst
	SLC 100 SILICONE CONCENTRATED YELLOW - Yellow concentrated
	pigment
	SLC 105 SILICONE CONCENTRATED GOLD - Gold concentrated pigment
	SLC 110 SILICONE CONCENTRATED ORANGE - Orange concentrated
	pigment SLC 115 SILICONE CONCENTRATED CARMINE RED - Carmine concentrated
	pigment
	SLC 120 SILICONE CONCENTRATED RED - Red concentrated pigment
	SLC 125 SILICONE CONCENTRATED MAGENTA - Magenta concentrated
	pigment
	SLC 130 SILICONE CONCENTRATED VIOLET - Violet concentrated pigment
	SLC 135 SILICONE CONCENTRATED BLUE - Blue concentrated pigment
	SLC 140 SILICONE CONCENTRATED GREEN - Green concentrated pigment SLC 145 SILICONE CONCENTRATED ULTRABLUE - Ultrablue concentrated
	pigment
	SLC 150 SILICONE CONCENTRATED BLACK - Black concentrated pigment
FEATURES	Excellent washing fastness
TEATORES	Excellent washing raseriess,
	Excellent working performance, Excellent elasticity feature,
	Excellent covering,
	Soft and silky touch,
	Compliance with ecological standards.
APPLICATION	: All products are used with %3 SLK 01 Silicone Catalyst. They have good
	potlife after adding catalyst.
	Except concentrated pigments, all products can be used after adding catalyst only.
	-
	Concentrated pigments can not be used only. They must be used with any
	carrier pasta like clear or white. Usage amount is maximum 5%.

	To obtain white puff pasta, SLC 15 WHITE can be added into SLC 20 PUFF between 15-25%.
	To obtain colourful puff pasta, SLC 20 PUFF can be mixed with SLC series concentrated pigments maximum 5%.
	Printed fabrics should be dried at 165C with 2 minutes
SCREEN	: For thick effects, 24T is suggested. For others 43T-90T can be used.
FIXING	: Curing time depends on the thickness of ink on the fabric. Fixing conditions between 160 -170°Cand 1,5 and 3 minutes.
CLEANING	: All materials and equipments can be cleaned by using white spirit after usage.

Note : Above mentioned qualified data is obtained from our R&D tests done in our own R&D labs. Supplied as General Knowledge and Information only and should not be considered as a Warranty Information.Printing Quality may change for different company conditions. Please start your production process after completing your own trial tests. Please stir before using the product and keep the product in room temperature.